



Trim Codes By Series

Series	Trim Code	Body		Disc		Stem	
		Material	Specification	Material	Specification	Material	Specification
393	140	Nodular Iron	ASTM A395	17-4	AMS 5355	17-4	AMS 5355
390	141	Cast Iron	ASTM A126 Class B	17-4	AMS 5355	17-4	AMS 5355
395	141	Cast Iron	ASTM A126 Class B	17-4	AMS 5355	17-4	AMS 5355
395	142	Cast Iron	NedoxCR+ / ASTM A126 Class B	NedoxCR+ / 17-4	AMS 5355	17-4	AMS 5355
395	143	Cast Iron	ASTM A126 Class B	NedoxCR+ / 17-4	AMS 5355	17-4	AMS 5355
400	162	Nodular Iron	ASTM A395	Alum Bronze	ASTM B-148 952	17-4	AMS 5643
422	162	Nodular Iron	ASTM A395	Alum Bronze	ASTM B-148 952	17-4	AMS 5643
400	163	Cast Iron	ASTM A126 Class B	Alum Bronze	ASTM B-148 952	17-4	AMS 5643
400	165	Cast Iron	ASTM A126 Class B	Nodular Iron / Epoxy Paint	ASTM A536	17-4	AMS 5643
422	166	Nodular Iron	ASTM A395	Nodular Iron / Epoxy Paint	ASTM A536	17-4	AMS 5643
400	168	Nodular Iron	ASTM A395	Nodular Iron	ASTM A536	17-4	AMS 5643
422	168	Nodular Iron	ASTM A395	Nodular Iron	ASTM A536	17-4	AMS 5643
400	169	Cast Iron	ASTM A126 Class B	Nodular Iron	ASTM A536	17-4	AMS 5643
400	170	Nodular Iron	ASTM A395	Nylon / NI	ASTM A536 (Base Mtl)	17-4	AMS 5643
422	170	Nodular Iron	ASTM A395	Nylon / NI	ASTM A536 (Base Mtl)	17-4	AMS 5643
400	171	Cast Iron	ASTM A126 Class B	Nylon / NI	ASTM A536 (Base Mtl)	17-4	AMS 5643
400/480	174	Aluminum*	*B26 Class B or 413 (3"-5")	Nodular Iron	ASTM A536	17-4	AMS 5643
400/480	175	Aluminum*	*B26 Class B or 413 (3"-5")	Alum Bronze	ASTM B-148 952	17-4	AMS 5643
400/480	176	Aluminum*	*B26 Class B or 413 (3"-5")	Nylon / NI	ASTM A536 (Base Mtl)	17-4	AMS 5643
390	177	Nylon / CI	ASTM A126 Class B	Nylon / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
399	177	Nylon / CI	ASTM A126 Class B	Nylon / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
392	178	ENP / NI	ASTM A395	Nylon / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
393	178	ENP / NI	ASTM A395	Nylon / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
390	179	ENP / CI	ASTM A126 Class B	Nylon / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
392	180	Nodular Iron	ASTM A395	Nylon / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
399	181	Cast Iron	ASTM A126 Class B	Nylon / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
390	182	Cast Iron	ASTM A126 Class B	Nylon / 17-4	AMS 5355	17-4	AMS 5355
400	190	Nodular Iron	ASTM A395	ENP / NI	ASTM A536 (Base Mtl)	17-4	AMS 5643
422	190	Nodular Iron	ASTM A395	ENP / NI	ASTM A536 (Base Mtl)	17-4	AMS 5643
400	191	Cast Iron	ASTM A126 Class B	ENP / NI	ASTM A536 (Base Mtl)	17-4	AMS 5643
390/380	255	Aluminum*	*B26 Class B or 413 (3"-5")	255	ASTM A890 1B	255	ASTM A890 1B
390	256	Nodular Iron	ASTM A395	255	ASTM A890 1B	255	ASTM A890 1B
393	256	Nodular Iron	ASTM A395	255	ASTM A890 1B	255	ASTM A890 1B
390	257	Cast Iron	ASTM A126 Class B	255	ASTM A890 1B	255	ASTM A890 1B
393	257	Cast Iron	ASTM A126 Class B	255	ASTM A890 1B	255	ASTM A890 1B
392	322	Nodular Iron	ASTM A395	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
393	322	Nodular Iron	ASTM A395	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
390	323	Cast Iron	ASTM A126 Class B	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
399	323	Cast Iron	ASTM A126 Class B	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
390/380	328	Aluminum*	*B26 Class B or 413 (3"-5")	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
399/389	328**	Aluminum*	*B26 Class B or 413 (3"-5")	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
392	332	SS 316	ASTM A351 CF8M	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
399	332	SS 316	ASTM A351 CF8M	316 S.F.	ASTM A351 CF8M	316	ASTM A351 CF8M
393	404	Nodular Iron	ASTM A395	Hypalon / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
390	405	Cast Iron	ASTM A126 Class B	Hypalon / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
393	432	Nodular Iron	ASTM A395	Buna / 4140	ASTM A193 B7 (Base)	17-4	AMS 5643
390	433	Cast Iron	ASTM A126 Class B	Buna / 4140	ASTM A193 B7 (Base)	17-4	AMS 5643
393	434	Nodular Iron	ASTM A395	Buna / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
390	435	Cast Iron	ASTM A126 Class B	Buna / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
393	452	Nodular Iron	ASTM A395	FKM / 4140	ASTM A193 B7 (Base)	17-4	AMS 5643
390	453	Cast Iron	ASTM A126 Class B	FKM / 4140	ASTM A193 B7 (Base)	17-4	AMS 5643
393	454	Nodular Iron	ASTM A395	FKM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
390	455	Cast Iron	ASTM A126 Class B	FKM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
390/380	493	Aluminum*	*B26 Class B or 413 (3"-5")	EPDM / 4140	ASTM A193 B7 (Base)	17-4	AMS 5643
393	494	Nodular Iron	ASTM A395	Carb-Nitrile / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
390	495	Cast Iron	ASTM A126 Class B	Carb-Nitrile / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
393	496	Nodular Iron	ASTM A395	EPDM / 4140	ASTM A193 B7 (Base)	17-4	AMS 5643
390	497	Cast Iron	ASTM A126 Class B	EPDM / 4140	ASTM A193 B7 (Base)	17-4	AMS 5643
392	498	Nodular Iron	ASTM A395	EPDM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
393	498	Nodular Iron	ASTM A395	EPDM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
390	499	Cast Iron	ASTM A126 Class B	EPDM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
399	499	Cast Iron	ASTM A126 Class B	EPDM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
392	522	Nodular Iron	ASTM A395	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
393	522	Nodular Iron	ASTM A395	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
390	523	Cast Iron	ASTM A126 Class B	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
399	523	Cast Iron	ASTM A126 Class B	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
390/380	528	Aluminum*	*B26 Class B or 413 (3"-5")	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
399/389	528**	Aluminum*	*B26 Class B or 413 (3"-5")	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
392	532	SS 316	ASTM A351 CF8M	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
399	532	SS 316	ASTM A351 CF8M	316 H.P.	ASTM A351 CF8M	316	ASTM A351 CF8M
392	721	Nodular Iron	ASTM A395	PTFE / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
399	722	Cast Iron	ASTM A126 Class B	PTFE / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
399/389	723**	Aluminum*	*B26 Class B or 413 (3"-5")	PTFE / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355



Trim Codes By Series

Series	Trim Code	Body		Disc		Stem	
		Material	Specification	Material	Specification	Material	Specification
392	731	SS 316	ASTM A351 CF8M	Halar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
399	731	SS 316	ASTM A351 CF8M	Halar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
392	732	SS 316	ASTM A351 CF8M	316	ASTM A351 CF8M	316	ASTM A351 CF8M
399	732	SS 316	ASTM A351 CF8M	316	ASTM A351 CF8M	316	ASTM A351 CF8M
392	734	SS 316	ASTM A351 CF8M	PTFE/ 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
399	734	SS 316	ASTM A351 CF8M	PTFE/ 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
392	735	SS 316	ASTM A351 CF8M	EPDM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
399	735	SS 316	ASTM A351 CF8M	EPDM / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
392	736	SS 316	ASTM A351 CF8M	Buna / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
399	736	SS 316	ASTM A351 CF8M	Buna / 17-4	AMS 5355 (Base Mtl)	17-4	AMS 5355
395	737	SS 316	ASTM A351 CF8M	17-4	AMS 5355	17-4	AMS 5356
392	810	Nodular Iron	ASTM A395 / ENP	316	ASTM A351 CF8M	17-4	AMS 5643
399	811	Cast Iron	ASTM A126 Class B / ENP	316	ASTM A351 CF8M	17-4	AMS 5643
392	822	Nodular Iron	ASTM A395	316	ASTM A351 CF8M	316	ASTM A351 CF8M
393	822	Nodular Iron	ASTM A395	316	ASTM A351 CF8M	316	ASTM A351 CF8M
390	823	Cast Iron	ASTM A126 Class B	316	ASTM A351 CF8M	316	ASTM A351 CF8M
399	823	Cast Iron	ASTM A126 Class B	316	ASTM A351 CF8M	316	ASTM A351 CF8M
400	824	Nodular Iron	ASTM A395	316	ASTM A351 CF8M	17-4	AMS 5643
422	824	Nodular Iron	ASTM A395	316	ASTM A351 CF8M	17-4	AMS 5643
400	825	Cast Iron	ASTM A126 Class B	316	ASTM A351 CF8M	17-4	AMS 5643
392	826	Nodular Iron	ASTM A395	Halar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
393	826	Nodular Iron	ASTM A395	Halar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
390	827	Cast Iron	ASTM A126 Class B	Halar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
399	827	Cast Iron	ASTM A126 Class B	Halar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
390/380	828	Aluminum*	*B26 Class B or 413 (3"-5")	316	ASTM A351 CF8M	316	ASTM A351 CF8M
399/389	828**	Aluminum*	*B26 Class B or 413 (3"-5")	316	ASTM A351 CF8M	316	ASTM A351 CF8M
400/480	829	Aluminum*	*B26 Class B or 413 (3"-5")	316	ASTM A351 CF8M	17-4	AMS 5643
390/380	830	Aluminum*	*B26 Class B or 413 (3"-5")	17-4	AMS 5355	17-4	AMS 5355
399	835	Cast Iron	ASTM A126 Class B	Hard Chrome / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
392	836	Nodular Iron	ASTM A396	Kynar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
393	836	Nodular Iron	ASTM A396	Kynar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
390	837	Nodular Iron	ASTM A395	Kynar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
399	837	Nodular Iron	ASTM A395	Kynar® / 316	ASTM A351 CF8M	316	ASTM A351 CF8M
390/380	855	Aluminum*	*B26 Class B or 413 (3"-5")	255 S.F.	ASTM A890 1B	255 S.F.	ASTM A890 1B
390	856	Nodular Iron	ASTM A395	255 S.F.	ASTM A890 1B	255 S.F.	ASTM A890 1B
393	856	Nodular Iron	ASTM A395	255 S.F.	ASTM A890 1B	255 S.F.	ASTM A890 1B
390	857	Cast Iron	ASTM A126 Class B	255 S.F.	ASTM A890 1B	255 S.F.	ASTM A890 1B
393	857	Cast Iron	ASTM A126 Class B	255 S.F.	ASTM A890 1B	255 S.F.	ASTM A890 1B
390	858	Cast Iron	ASTM A126 Class B	255	ASTM A890 1B	255	ASTM A890 1B
400	8P4	Nodular Iron	ASTM A395	316/Halar®/Alloy 20 DSCRW	ASTM A351 CF8M	17-4	AMS 5643
422	8P4	Nodular Iron	ASTM A395	316/Halar®/Alloy 20 DSCRW	ASTM A351 CF8M	17-4	AMS 5643
* 3", 4", and 5" ALUMINUM BODY VALVES ARE DIE CAST A413 ALUMINUM. 2" and 6-12" ARE ASTM B26 CLASS B ALUMINUM.							
** NOT AVAILABLE IN 3"							